

Tarpaper Recycling ApS
Naverland 2
17. sal
DK 2600 Glostrup
DENMARK

Date: 16 January 2025
Test Report Ref: TR 1092054

Page 1 of 1

Contract: Recycled Material Testing

LABORATORY TEST REPORT


TEST REQUIREMENTS:

To determine the Composition Analysis in accordance with **BS EN 12697 -1: 2020 (Annex B Procedure 2) & 2: 2015 + A1 2019**

SAMPLE DETAILS:

Certificate of sampling received:	Sample Details on Tubs	Name of Source:	Tarpaper Recycling
Laboratory Ref. No:	S128689	Method of Sampling:	Unknown
Client Ref. No:	Sample 5	Sampled By:	Client (Test results apply to sample as received)
Date of Receipt at Lab:	03/01/2025	Tested By:	KF/KF/CH
Date of Start of Test:	14/01/2025	Ticket No/Vehicle Reg:	Unknown
Sampling Location:	Unknown	Sample Temperature:	Unknown
Material Description:	Roofing felt		
Target Specification:	Unknown		
Date and Time of Sampling:	Produced - 01/12/2024 to 15/12/2024		

Results



BS Test Sieve Size	Percentage By Mass Passing	Specification Limits
6.3 mm	100	-
4.0 mm	100	-
2.0 mm	72	-
1.0 mm	71	-
0.500 mm	68	-
0.250 mm	64	-
0.125 mm	61	-
0.063 mm	52.9	-
Binder Content(%)	61.6	-

This test report shall not be reproduced, except in full, without the written approval of Celtest Company Limited.

These results relate only to the items tested.

Comments:

no material specification supplied

Report checked and approved by:



Rodney Roberts
Asphalt Team Manager

Tarpaper Recycling ApS
Naverland 2
17. sal
DK 2600 Glostrup
DENMARK

Date: 16 January 2025
Test Report Ref: TR 1092053

Page 1 of 1

Contract: Recycled Material Testing


LABORATORY TEST REPORT

TEST REQUIREMENTS: To determine the Composition Analysis in accordance with BS EN 12697 -1: 2020 (Annex B Procedure 2) & 2: 2015 + A1 2019

SAMPLE DETAILS:

Certificate of sampling received:	Sample Details on Tubs	Name of Source:	Tarpaper Recycling
Laboratory Ref. No:	S128689	Method of Sampling:	Unknown
Client Ref. No:	Sample 4	Sampled By:	Client (Test results apply to sample as received)
Date of Receipt at Lab:	03/01/2025	Tested By:	Unknown
Date of Start of Test:	14/01/2025	Ticket No/Vehicle Reg:	Unknown
Sampling Location:	Unknown	Sample Temperature:	
Material Description:	Roofing felt		
Target Specification:	Unknown		
Date and Time of Sampling:	Produced - 15/11/2024 to 30/11/2024		

Results



BS Test Sieve Size	Percentage By Mass Passing	Specification Limits
6.3 mm	100	-
4.0 mm	100	-
2.0 mm	70	-
1.0 mm	69	-
0.500 mm	65	-
0.250 mm	61	-
0.125 mm	58	-
0.063 mm	49.3	-
Binder Content(%)	58.6	-

This test report shall not be reproduced, except in full, without the written approval of Celtest Company Limited.

These results relate only to the items tested.

Comments:
The grading analysis complies with specification requirements
The binder content complies with specification requirements

Report checked and approved by:

Rodney Roberts
Asphalt Team Manager